



Aurous 19

Chromate

1. Description

Aurous 19 is a QPL approved and listed powdered chemical used to form a protective conversion coating on aluminum surfaces which minimizes corrosion and provides an improved bond for painting.

- QPL approved and listed.
- Mil-C-5541
- Document ID Mil-DTL-81706B, Type I, Class 1A, Form II, Method C
- Document ID Mil-DTL-81706B, Type I, Class 3, Form II, Method C

2. Application instructions

To ensure a uniform coating, the aluminum surface must be clean and deoxidized.

	<u>Class 1A</u>	<u>Class 3</u>
Concentration:	1.5-2.0 oz/gal	0.30-1.0 oz/gal
pH:	1.4-1.9	1.9-2.6
Temperature:	65-80°F	65-80°F
Immersion time:	2-4 minutes	1-3 minutes

3. Conditions for using Aurous 19

- Tank: Tanks should be made of stainless steel, polyethylene, PVC or equal.
- pH adjustments: Lower with nitric acid-67% (42 Baume).
Raise with dilute ammonium hydroxide.
Avoid quick additions.
- Agitation: Moderate agitation improves coating uniformity.
- Rinsing: Drag in of acid or alkaline material is detrimental to the Aurous 19 solution. Ensure rinsing prior to the passivation step is thorough.
- Drying: Drying is accomplished by clean air blast, centrifuge or warm circulating air.
Avoid temperatures exceeding 140°F.
Setting or hardening begins immediately after drying.
Allow 24 hours of hardening time prior to wrapping or corrosion resistance testing to ensure consistent results.

4. Solution makeup

1. Fill tank $\frac{3}{4}$ full with water.
2. Add the required amount of Aurous 19 while stirring.
3. Add remaining water to final volume.
4. Adjust solutions pH if necessary.

5. Titration procedure

Reagents: 0.1N sodium thiosulfate
50% sulfuric acid
10% potassium iodide solution
1% starch indicator

- Procedure:
1. Pipette 10-ml of sample into 500 Erlenmeyer flask.
 2. Dilute 10-ml sample with water to 250 ml mark.
 3. Add 10-ml of potassium iodide solution.
 4. Add 5-ml of sulfuric acid.
 5. Titrate with 0.1N sodium thiosulfate to a light-yellow color.
 6. Add 2-ml starch indicator.
 7. Continue titration drop by drop with constant stirring until solution turns clear.

Calculation: ml of sodium thiosulfate x .08 = oz/gal Aurous 19

6. Storage

Store in original container in a cool dry location.
In humid environments, powder/granule will harden.
Keep away from flammables and acids.

7. Packaging

10 lb.
100 lb.

8. Product safety

We recommend that the company/operator read and review the **Safety Data Sheet** for the appropriate health and safety warnings before use.

U.S. Specialty Color Corporation® recommendations, notices or instructions as to handling, use, storage of any product, including its use alone or in combination with other products, or as to any apparatus or process for the use of any product, are based upon information believed to be reliable, but U.S. Specialty Color Corporation® shall have no liability with respect to any recommendations or instructions. U.S. Specialty Color Corporation® sole and exclusive warranty is that its products comply with U.S. Specialty Color Corporation® published chemical and physical specifications. U.S. Specialty Color Corporation® makes no other warranties, other express or implied with respect to its recommendations, instructions, products, apparatus, and process or otherwise and specifically disclaims any implied warranties of merchantability, suitability, fitness for a particular or otherwise.